

Sonneborn Building Products Division

Corporate Headquarters 889 Valley Park Drive Shakopee, MN 55379 Phone: 612/496-6000

January 20, 1995

Coverdeck Systems Paul L. Betty, President 440 Copper Drive Newport, DE 19804

Dear Paul;

We have tested our waterproofing membrane products, HLM 5000 and Sonoguard, for compatibility with the Coverdeck system. Project identification numbers: 9.001.5/1.005. /1.008.

The materials were cast and cured for one day at standard conditions and placed in a sealed container with the Coverdeck on top. The materials were evaluated at one, two, five, and seven days for any discoloration or deterioration of the coating or the Coverdeck material. No sign of discoloration or deterioration was noticed with either membrane or the Coverdeck.

The conclusion of this test is complete compatibility between the various products.

Properly applied HLM or Sonoguard will perform as warranted in conjunction with a Coverdeck application.

Sincerly,

Gene Bollinger

Senior Product Manager

cc. Tech service Salesforce